

Product data sheet	
Product range	Bennett & Jones 14 mm

Product data	
Dimensions in mm (L * W * T)	plank 1900 x 190 x 14
Wear surface	approx. 3,0 mm
Units / package	8 pieces
Package	2,889 m ² ; 22,5 kg
Warranty	15 years for private use according to our terms of warranty
Connection	Click 2G
Notes	Subject to technical changes, Cleaning and care see instructions please

Product constructions	
Wear surface	Hardwood
Middle layer	softwood staves
Stabilizing layer	poplar

Product properties	
	Test norm
Thermal resistance	DIN EN 4108-4 0,13W/mK
Biological durability	class 1
PCP content	≤5 ppm
Formaldehyde emission	EN 717 - 2 E1
Reaction to fire	EN 13501-1 Dfl-s1
Resistance to chair castors	DIN EN 13329 No impact if soft chair castors are used
Sorting requirements	EN 13489 Requirements are met by factory sorting
Laying system	EN 13489 floating, overall glued
Floor heating	Only suitable for hot water underfloor heating with a maximum surface temperature of 29°C
Renovation	At least resandable twice with normal wear
Disposal	Private disposal in the garbage possible

Tolerances according to EN 13489

allowed differences in width	± 0,2 mm
allowed differences in squareness	≤ 0,2 %
longitudinal curvature	≤ 0,1 %
Transverse curvature	≤ 0,2 %
Differences in height	≤ 0,2 mm
Humidity level on delivery	5-9%

Other packaging properties	Each pack can contain one board in two pieces (plank format)
----------------------------	--

Surface properties				
	Test norm	laquered	natural oil treated	natural oil treated, brushed
slip resistance	EN 15676	USRV 70	USRV 57	USRV 94
Resistance to staining	DIN 68861 - 1	1B	1C	1C
Scratch resistance	Hamberger Hobe	≥ 20 N	n.n	n.n

Due to its lively appearance, the grading is quite separate from conventional grading criteria. Knots and splits are desirable visual characteristics of the grading, which when subjected to climate fluctuation can lead to the formation of cross going cracks